

PA 910

Alloy 910, Nylon 6/69
Polyamide Copolymer

Print Settings	
Extruder Temperature	265°C
Bed Temperature	70°C
Bed Preparation	WolfBite Nitro
Cooling Fan	Yes
Closed Chamber	Yes
Heated Chamber	Yes
Chamber Temperature	Default
Notes	

Material Management	
Drying	<ul style="list-style-type: none"> Not available from Airwolf
Recommended Support Material	<ul style="list-style-type: none"> N/A
Storage	<ul style="list-style-type: none"> Store in a dry place.
Compatible Materials	<ul style="list-style-type: none"> None

Slicer Settings	APEX
Material Profile Name	910 Nylon
Layer Height	0.2 mm
Nozzle Diameter	0.5 mm
Loops	0.6
Skin	1 mm
Infill	42%